*TENCATE Tecashield

EMERGENCY RESPONSE

The TenCate Tecashield® collection is a range of inherently heat- and flame-resistant fabrics.

KR 610 - 545 g/m² (Arashield™)

Inherently heat- and flame-resistant fabric Reinforcement: para-aramid with high solid double face polymer coating

The TenCate Tecashield[®] - KR 610 (Arashield[™]) is lighter yet stronger than other reinforcement materials, such as leather. This fabric is to be applied in places where exposure to abrasion is highest e.g. knees and elbows. Due to the combination of 100% para-aramid woven fabric with a high solid polymer double face coating this fabric has exceptional strength and thermal protection.

Outstanding value – Suitable for application as reinforcement for fire fighters turnout gear, military combat suits and protective clothing for law enforcement and the metal sector.

Excellent thermal performance – Withstands extreme temperatures due to high solid polymer coating on both sides of the fabric.

Optimal comfort – Maximum flexibility due to the combination of the woven fabric and high solid polymer coating.

Liquid chemicals and water protection – Excellent protection against water and hazardous liquid chemicals.

Unbeatable durability – The fabric has exceptional resistance to abrasion and has been thoroughly tested for its protective properties and has also been submitted to an extensive range of washing and wearing tests at independent testing institutes.

Superior cut and puncture resistant – Complies with EN 388: 2003. **Complete system** – TenCate is able to supply all the components of the fire fighters turn out gear: outer shell, moisture barrier, thermal barrier, thermal liner, reinforcement and cuffs.





*TENCATE Tecashield

EMERGENCY RESPONSE

The TenCate Tecashield® collection is a range of inherently heat- and flame-resistant fabrics.

Technical data	TenCate Tecashield®	Test method	Standard colours	
Quality	KR 610 (Arashield™)		KR Black KR Grey	
Width	153 cm (+2/-1 cm)	ISO 3801: 1978	90042 90039	
Weight	545 g/m² (± 10%)	ISO 3932: 1980		
Composition	Para-aramid with high solid polymer coating		KR Gold	
Protection	Reinforcement		90041	
Tensile strength	2000 N x 700 N (± 10%)	ISO 13934-1: 1999		
Martindale abrasion	> 100.000	ISO 12947-2: 2002	The colours above are standard colours and available with a minimum order length of 50 metres. The colours shown are a reference only.	
Laundry shrinkage	0,5 x 0,5	ISO 5077: 2007		
PPE* requirements				
Washing symbols	19 🖄 🖸 🖂 🖻			
Certification				
- 0	Firefighting	EN 469: 2005	* Copyright symbols: NEN, Delft (Netherlands)	
	Heat and flame retardancy	EN ISO 11612 A1, A2, B2, C1, E3: 2008	** After pre-treatment (five wash/dry cycles according	
	Welding	EN ISO 11611, class 1: 2007 EN 470-1: 1995	to EN ISO 6330: 2000. Procedure 2A (60°C) with	
<u> </u>	Protection from mechanical risks: abrasion, blade cut, tear and puncture resistance.	EN 388: 2003, EN 530: 1995	tumble drying (Procedure E) (max. 70°C outlet temperature *** As received	

Results EN 469: 2005						
Property	Test method	EN 469 requirements	Results obtained	PASS/level		
6.1 Flame spread	EN ISO 15025: 2002 Procedure A	EN 533 index 3: No flaming to edge - No hole formation - No flaming or molton debris - Mean afterflame ≤ 2s - Afterglow not to spread	EN 533 index 3: No flaming to edge - No hole formation - No flaming or molton debris - No afterflame - No afterglow	PASS**		
6.5 Heat resistance	ISO 17493: 2000 at 180 °C	Materials shall not ignite or melt Shrinkage $\leq 5\%$	Material did not ignite or melt. Shrinkage < 1%	PASS***		



Member of the E.T.S.A.

TenCate Protective Fabrics

TenCate is the world's No. 1 producer of protective fabrics for the manufacturing of safety wear. We supply garment-makers with an extensive range of top-quality and technologically advanced fabrics.

Our fabrics become lifesaving garments for firefighters, industrial workers, military personnel and other professionals working under hazardous conditions in danger zones around the world.

We work closely with our customers, end-users, fibre and chemical manufacturers and independent laboratories. As a result, TenCate Protective Fabrics is the one source the world looks to for leadership in knowledge of materials, consistent product quality, and a proven commitment to service excellence.

TenCate is a trademark of Royal Ten Cate nv. Tecasafe is a trademark of Ten Cate Protect bv. Ten Cate Protect bv is a subsidiary of Royal Ten Cate nv.



TEN CATE PROTECT BV TenCate Protective Fabrics P.O. Box 186 7440 AD Nijverdal The Netherlands Tel. +31 (0)548 633922 Fax +31 (0)548 633256 E-mail: protectivefabrics@tencate.com www.tencateprotectivefabrics.com